

A thick dark grey vertical bar runs down the left side of the page. To its right, several thin, curved lines in black and grey sweep upwards and to the right, creating an abstract, organic shape.

GLAZE PLUS

# TECHNICAL DATA SHEET

GLAZE PROFILL-900

## GLAZE PROFILL-900



### DESCRIPTION

GLAZE PROFILL-900 is polymer modified cement based non sanded grout which is ideal for fitting & finishing of all types of tiles, marble and stone's joints in interior or exterior for both floors & walls, grouting of joint treatment with resistant water type joint.

### USES

- Vitrified tile
- Marble
- Natural stone
- To fill the tile joints with grout so as to create strong long lasting tile joints

### ADVANTAGES

- Extra fine finish
- High resistant to sunlight
- Easy to clean

- High performance grout
- Excellent water resistance
- Designed for grouting wall & floor tiles, marbles, & stones etc.
- Natural antibacterial

## COMPLIANCE STANDARD

EN 12004:2019

## METHOD OF APPLICATION

- Clean tile joint from all dusts, oils etc. and the joint should be dry.
- Mix 320 ml of clean water to 1 Kg of GLAZE PROFILL-900. If we are adding POLY GROUT then water content may reduce to 80 to 100 ml.
- Apply GLAZE PROFILL-900 firmly to ensure that the tile spaces are completely filled.
- Remove surplus grout and Allow grout to firm up then smooth the joints by wiping with slightly damp cloth or sponge.

## TECHNICAL INFORMATION

| Properties              | Results                                   |
|-------------------------|---|
| Pot life @ 20°C         | 4 hours                                   |
| Pot life @ 20°C         | 3 hours                                   |
| Mixed Density           | 1.90kg/liter (brush able Consistency)     |
| Tensile strength        | 2 N/ mm <sup>2</sup> (at 1.5mm Thickness) |
| Colors                  | Shed card available                       |
| Application temperature | Not less than 10°C                        |
| Toxicity                | Non-toxic                                 |
| Adhesion to Concrete    | >1N/mm <sup>2</sup>                       |

GLAZE PROFILL-900 has a shelf life of 12 months if kept in a cool and dry place in unopened bags under room temperature (i.e. 27°C)

## PACKAGING

- 1Kg

## TECHNICAL SUPPORT

9/47 Subhash Nagar, New Delhi 110027 | C401 - Swami Narayan Business Park, Narol Circle Ahmedabad - 382405 | [www.glazeplusitaly.com](http://www.glazeplusitaly.com), [www.glazeplus.in](http://www.glazeplus.in) | [sales@glazeplus.in](mailto:sales@glazeplus.in)  
Helpline no. +91836807749